



# UTILI-T™ SPRAY ENAMELS

## DESCRIPTION AND USES

UTILI-T™ Spray Enamel is an all-purpose spray paint designed to provide a durable protective coating that resists fading, chipping, and peeling. These sprays apply easily and dry fast to a tough attractive finish. Not for use on galvanized metal.

## PRODUCTS

SKU	DESCRIPTION (10 oz. Aerosol)
387389	Flat Black
387390	Gloss Black
387391	Gloss Red
387392	Gloss Yellow
387393	Gloss Green
387394	Gloss Blue
387395	Gloss White
387396	Aluminum
387397	Gray Primer
387398	Gloss Orange
387399	Flat White
387400	Gloss Dark Gray
399360	WM-Green
399361	WM-Gold

## PRODUCT APPLICATION

### SURFACE PREPARATION

Remove all dirt, grease, oil, salt, and chemical contaminants by washing the surface with a commercial detergent like Rust-Oleum® Professional Cleaner Degreaser, or other suitable cleaning method. Rinse with fresh water and allow to thoroughly dry. Remove loose paint and rust with a wire brush or sandpaper. Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile.

**WARNING!** If you scrape, sand, or remove old paint from any surface, you may release lead paint dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

## PRODUCT APPLICATION (cont.)

### APPLICATION

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C). Do not apply to galvanized steel. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 10-12" from surface and spray in a steady back and forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply 2-3 light coats a few minutes apart to avoid drips and runs. **Do not use near open flame.**

### DRY & RECOAT

Dry and recoat times are based on 77°F (21°C) and 50% relative humidity. Allow more time at cooler temperatures. Dries to the touch in 2 hours, dries to handle in 8 hours and is fully dry in 24 hours. Recoat within 1 hour or after 24 hours.

### CLEAN-UP

Clean valve immediately after use by turning can upside down and depressing spray button for 3-5 seconds (some paint will be sprayed out, so be careful to not inadvertently spray yourself or other objects). Clean up wet paint with xylene or mineral spirits. Throw away empty can in trash pick-up. Do not burn or place in home trash compactor.

### CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.



# UTILI-T™ SPRAY ENAMELS

## PHYSICAL PROPERTIES

		UTILI-T SPRAY ENAMELS
<b>Resin Type</b>		Alkyd
<b>Pigment Type</b>		Varies with color
<b>Solvents</b>		Acetone, N Butyl Acetate, Aromatic, Aliphatic
<b>MIR</b>	<b>Primer</b>	0.70 Max
	<b>Flat</b>	0.80 Max
	<b>Gloss</b>	0.95 Max
	<b>Metallic</b>	1.25 Max
<b>Fill Weight</b>		10 ounces
<b>Practical Coverage at Recommended DFT (assumes 15% material loss)</b>		Approximately 2-4 sq.ft./can (0.19-0.37 m <sup>2</sup> /can)
<b>Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity</b>	<b>Touch</b>	2 hours
	<b>Handle</b>	8 hours
	<b>Recoat</b>	Within 1 hour or after 24 hours
	<b>Full Cure</b>	24 hours
<b>Dry Heat Resistance</b>		200°F (93°C)
<b>Shelf Life</b>		5 years
<b>Flash Point</b>		-156°F (-104°C)
<b>Safety Information</b>		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.