



Eclectic Products LLC  
Manufacturing Facility  
101 Dixie Mae Drive  
Pineville, Louisiana  
eclecticproducts.com  
**800.349.4667**

ISO 9001:2015  
Compliant Quality  
Management  
Systems

Administration Office  
Eugene, Oregon  
eclecticproducts.com  
**800.693.4667**

## United States



25 fl oz pouch  
(2 pouches per box)



Scan to view the  
ProCRETE website

## PROCRETE® PREMIUM ASPHALT REPAIR POTHOLE & CRACK REPAIR

**PROCRETE PREMIUM ASPHALT REPAIR** is a superior quality 2-component urethane patch for damaged asphalt repair and restoration. It provides an all-weather repair for cracks and holes, and prevents further damage or water penetration. Unlike asphalt, it will not crack, shrink or lose its adhesion to the repaired area – even after years of severe weather. The easy-flow formula thickens as it cures for added structure, making it the perfect fix for deep repairs, while still allowing easy flow into cracks and crevices. Helps prevent trip and fall accidents! **THE ONCE-AND-DONE PERMANENT SOLUTION!**

### WHERE TO USE / APPLICATIONS

Horizontal Application On: potholes / cracks / playgrounds and parks / parking lots / driveways / roads / airport tarmacs and more!

### FEATURES AND BENEFITS

- 10X tougher than cold patch and trowel patch products!
- Made with the same urethane technology as specified by structural bridge, airport and highway engineers
- Deep patch repair – fill up to 10 feet
- Maintains its integrity when exposed to deicing salts used on roads to improve traction and safety in winter environments.
- Interior / exterior
- Easy to use - mix right inside the pouch
- Remains intact and permanent through freeze/thaw and extreme heatcycles year-after-year
- Drive over ready/return to service as soon as 2 hours
- Crush resistant

### TECHNICAL INFORMATION

|                                |                                                                                                                                  |
|--------------------------------|----------------------------------------------------------------------------------------------------------------------------------|
| Color:                         | Black                                                                                                                            |
| VOC:                           | <0.5 g/L as mixed                                                                                                                |
| Working Time:                  | 15 – 20 min at 70 °F (from start of mixing)                                                                                      |
| Cure Time/Open To Traffic:     | 2 hours at 70 °F (minimum). Higher temperatures will speed up cure; lower temperatures slow down cure.                           |
| Water Resistant:               | Yes                                                                                                                              |
| Ideal Application Temperature: | 70 to 80 °F                                                                                                                      |
| Service Temperature Range:     | Fully cured product can withstand temperatures from -40 to 212 °F intermittently.                                                |
| Storage:                       | Store in clean, dry, cool, low-humidity and shaded environment between 50 to 90 °F.                                              |
| Shelf Life:                    | 3 years                                                                                                                          |
| Freeze/Thaw Stability:         | Yes, tested up to 50 freeze/thaw cycles.                                                                                         |
| Paintable:                     | Yes, oil-based paints recommended. Test first to ensure compatibility and adhesion.                                              |
| Clean up:                      | Tools can be cleaned with soap and water, wiping off uncured material, or scraping cured product. Wash skin with soap and water. |

# PROCRETE® PREMIUM ASPHALT REPAIR

## POTHOLE & CRACK REPAIR

### COVERAGE INFORMATION

| Pouch Size      | Square Coverage                                                                                      | Linear Coverage                                                                       |
|-----------------|------------------------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------|
| 25 fl oz pouch: | 0.31 ft <sup>2</sup> x 1 in D<br>0.62 ft <sup>2</sup> x 0.5 in D<br>1.25 ft <sup>2</sup> x 0.25 in D | 3.75 ft x 1 in W x 1 in D<br>7.5 ft x 1 in W x 0.5 in D<br>15 ft x 1 in W x 0.25 in D |

### ASTM RESULTS

| Description                                    | Results                         | ASTM  |
|------------------------------------------------|---------------------------------|-------|
| Adhesion to Asphalt                            | 350 psi, 100% substrate failure | D7234 |
| Abrasion Resistance, H-18 Wheel, 2,000g weight | 210mg lost / 500 cycles         | D2369 |
| Compression Strength, 2" Cube, 24 Hour Cure    | 20,000 psi                      | C579  |
| Tensile Strength, Full Cure                    | ≥ 2,080 psi                     | D412  |
| Elongation, Full Cure                          | ≥ 51 %                          | D412  |
| Wet Bond Strength to Concrete, UNPRIMED        | 330 psi                         | C307  |
| Adhesion to Concrete                           | >500 psi                        | D4541 |
| Shore D Hardness                               | 53-55                           | D2240 |
| Solids Content                                 | 99.9%                           | D2369 |
| Viscosity (Resin)                              | 2,600 cSt                       | D445  |

### DIRECTIONS AND APPLICATION NOTES

**IMPORTANT:** Read directions thoroughly before use. High temperatures greatly affect cure time and pouch heat! Ensure pouch is at room temperature (approximately 70 °F / 21 °C) or cooler before mixing. Do not burst, mix or open pouch until ready to use! Wear disposable gloves & eye protection. Use entire contents immediately after mixing.

**STEP 1: PREP MATERIAL.** Concrete surface to be repaired must be older than 28 days, structurally sound, clean and DRY. Remove dirt, loose particles, or remnants of prior repairs from area to be patched. Brush/scrape area clean or blow clean with compressed air. If area to be repaired contains oil or grease, clean and dry thoroughly before patching. If necessary to stop product from absorbing into ground, block bottom of repair with backer rod or dry sand. **Do not add additional aggregate material during the mixing process.**

**STEP 2: BURST POUCH.** Massage contents in **Side A** only for 1 minute (without bursting the middle divider). Then, roll the contents of **Side A** until it bursts the middle divider and mixes with **Side B**.

**STEP 3: MIX.** Mix pouch contents thoroughly by massaging the pouch for approximately 4 minutes. Best technique for thorough mixing: Knead product up and down and side-to-side throughout both chambers repeatedly. The pouch will become hotter as you knead it. When it is hot to the touch, dispense immediately. **WORKING TIME:** Workable for approximately 15-20 minutes depending on ambient temperature (from start of mixing).



## PROCRETE® PREMIUM ASPHALT REPAIR

### POTHOLE & CRACK REPAIR

#### DIRECTIONS AND APPLICATION NOTES *Continued*

**STEP 4: DISPENSE.** Roll up pouch (starting from the bottom of **Side A**) pushing material to top of pouch. Carefully cut the upper corner where indicated. Continue to roll the pouch, pushing/squeezing the mixed product into the center of the repair.

**STEP 5: REPAIR.** Product will self-level in the repair. Trowel/knife if necessary. If desired, after dispensing the product, add dry topping sand to match the surrounding area before product is fully cured (should still be tacky). **NOTE:** Do not touch material with bare hands.

#### HEALTH AND SAFETY

Before working with this product, read and become familiar with information concerning hazards, proper use and handling.  
To request a Safety Data Sheet, please email [sds@eclecticproducts.com](mailto:sds@eclecticproducts.com).

#### LIMITED WARRANTY

The product is warranted against any defect in materials or workmanship under normal use for a period of 180 days after the date of purchase. The product is also warranted under any implied warranties provided under applicable law, including, without limitation, the implied warranty of merchantability and the implied warranty of fitness for a particular purpose, for a period of 180 days after the date of purchase. The manufacturer will not accept liability for more than product replacement. This warranty covers only the original buyer of the product. For warranty service, the buyer should contact the store where the product was purchased, or write Eclectic Products LLC, P.O. Box 4450, Pineville LA 71361 or call 800.767.4667. Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and compensation for any other reasonably foreseeable loss or damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure. This warranty gives you specific legal rights, and you also have other rights, which vary from province to province.